

## TENDRAIN 370-2 Double-Sided Geocomposite (expansion)

The drainage geocomposite is comprised of a tri-axial geonet structure with thermally bonded non-woven geotextiles on both sides. The product is capable of providing high Transmissivity in a soil environment under sustained normal loads and will have properties conforming to the values and test methods listed below.

PROPERTY	TEST METHODS	UNITS	VALUE	QUALIFIER	TEST FREQUENCY
<b>Resin</b>					
• Density	ASTM D 1505	g/cm <sup>3</sup>	0.94	MAV	lot
• Melt Flow Index	ASTM D 1238	g/10min	1.0	MAX	lot
<b>Geonet Core<sup>1</sup></b>					
Structure <sup>2</sup>			Tri-axial		
• Geonet Cross-Rib Spacing	Calibered	inch (mm)	0.43 (11.0)	MAX	50,000 sf
• Geonet Main-Rib Spacing	Calibered	inch (mm)	0.47 (12.0)	typical	50,000 sf
• Unsupported Aperture Area		inch <sup>2</sup> (mm <sup>2</sup> )	0.3 (195)	MAX	50,000 sf
• Tensile Strength – MD	ASTM D 4595	lb/ft (kN/m)	625 (9.0)	±10 %	50,000 sf
• Creep Reduction Factor <sup>3</sup> @ 4,000 psf, 20 °C	GRI - GC8	-	1.2		
• Thickness	ASTM D 5199	mil (mm)	250 (6.3)	±10 %	50,000 sf
• Carbon Black	ASTM D 4218	%	2-3	range	50,000 sf
<b>Geotextile<sup>1</sup></b>					
• U.V. Resistance (500 hrs)	ASTM D 4355	%	70		Per formula
• Serviceability Class	AASHTO M-288		Class 2		
• Grab Tensile	ASTM D 4632	lbs (N)	160 (712)	MARV	100,000 sf
• Grab Elongation	ASTM D 4632	%	50	MARV	100,000 sf
• Tear Strength	ASTM D 4533	lbs (N)	60 (267)	MARV	100,000 sf
• Puncture Resistance	ASTM D 4833	lbs (N)	85 (378)	MARV	100,000 sf
• AOS <sup>4</sup>	ASTM D 4751	US Sieve (mm)	70 (0.212)	MaxARV	500,000 sf
• Permittivity <sup>4</sup>	ASTM D 4491	Sec <sup>-1</sup>	1.1	MARV	500,000 sf
<b>Geocomposite</b>					
• Roll Sizes	12.5 ft x 200 ft (3.8 m x 61 m)				
• Peel Adhesion – MD	ASTM D 7005	lb/in (g/in)	1.0 (454)	MAV	100,000 sf
• Transmissivity <sup>5</sup> - MD Gradient / Load	ASTM D 4716 GRI - GC8	m <sup>2</sup> /sec	<u>10,000 psf</u> (480 kPa)	MAV	200,000 sf
0.1			1.0*10 <sup>-3</sup>		

Qualifiers: MARV=Minimum Average Roll Value (MARV), MAV=Minimum Average Value, MAX=Maximum Value, MaxARV=Maximum average roll value.

NOTES: **1.** Geotextile and geonet properties listed are prior to lamination. **2.** Tri-axial geonet consists of thick main-ribs with diagonally placed top and bottom-ribs. **3.** Creep Reduction Factor is based on 10,000 hour test duration, extrapolated to 30 years, under the corresponding compressive load and temperature. **4.** Hydraulic properties: AOS and permittivity are only applicable to the top filter geotextile. **5.** Geocomposite transmissivity measured by manufacturer per ASTM D4716 with testing boundary conditions as follows: steel plate / Ottawa sand / geocomposite / 60 mil HDPE geomembrane / steel plate, and seating period of 100 hours according to GRI-GC8, with the stronger side of the geocomposite facing the soft boundary condition as indicated with top (soil) /bottom (liner) label on the rolls. Digital indicator of hydraulic gradient is required during the transmissivity measurement at low gradients.